

<i>Sili30</i>	<i>Silikon 30°±5 Shore A, blau, Stärke: 1mm, 1,5mm, 2mm, 3mm, 4mm, 5mm</i>	<i>Stand: 28.11.2019</i>
Härte (Shore A) DIN 53505:	30° ± 5 Shore A	
Farbe:	Blau	
Dichte (g/cm³) DIN 53479:	1,13	
Temperaturbereich:	-40 bis + 200 °C	
Ozonbeständigkeit:	gut	
Beständigkeit tierische, pflanzliche und mineralische Öle und Fette:	nicht empfohlen	
Säurebeständigkeit:	nicht empfohlen	
Basenbeständigkeit:	bedingt	
Kraftstoffbeständigkeit:	nicht empfohlen	
Zulassungen:	FDA konform 177.2600, BFR XV konform, WRAS, EU 1935/2004, REACH und ROHS konform	
Bemerkungen:	Peroxid vernetzt, talkumiert	

Jederzeitige Änderungen vorbehalten.

Alle in diesem technischen Datenblatt erhaltenen Angaben stellen Richtwerte dar, welche sich als langjährige Durchschnittswerte erprobt haben.

<i>Sili 30</i>	<i>Silicon 30°±5 Shore A, blue, thickness: 1mm, 1,5mm, 2mm, 3mm, 4mm, 5mm</i>	<i>date: 28.11.2019</i>
hardness (Shore A) DIN 53505:	30° ± 5 Shore A	
color:	Blue	
density (g/cm³):	1,13	
temperature range:	-40 to + 200° C	
ozone resistance:	good	
vegetable, animal and mineral oil and fats resistance:	not recommended	
acid resistance:	not recommended	
base resistance:	conditional	
petrol resistance:	not recommended	
permissions:	FDA konform 177.2600, BFR XV konform, WRAS, EU 1935/2004, REACH und ROHS konform	
remarks:	peroxid linked, talcum	

Subject to alteration without prior notice.

All mentioned properties contained in this technical data sheet are guiding values representing longterm experience average.