

*225/NovaFlex      Novapress Flexible 815, grün/natur, Stärke 0,5 bis 3 mm      Stand: 03.02.2017*

<b>Farbe:</b>	grün	
<b>Dichte (g/cm<sup>3</sup>) :</b>	1,35	
<b>Betriebsdruck max.:</b>	50 bar	
<b>Kompressibilität:</b>	ASTM F 36 J	6-14 %
<b>Rückfederung:</b>	ASTM F 36 J	>55 %
<b>Zugfestigkeit:</b>	8 Mpa	
<b>Ölbeständigkeit:</b>	sehr gut	
<b>Benzinbeständigkeit:</b>	gut	
<b>Säurebeständigkeit:</b>	nicht empfohlen	
<b>Laugenbeständigkeit:</b>	bedingt	
<b>Zulassungen:</b>	DVGW, BAM	

Jederzeitige Änderungen vorbehalten.

Alle in diesem technischen Datenblatt erhaltenen Angaben stellen Richtwerte dar, welche sich als langjährige Durchschnittswerte erprobt haben.

<i>225/NovaFlex</i>	<i>Novapress Flexible 815, green/natural, thickness 0,5 to 3 mm</i>	<i>date: 03.02.2017</i>
<b>color:</b>	green	
<b>density (g/cm<sup>3</sup>):</b>	1,35	
<b>operating pressure max.:</b>	50 bar	
<b>compressibility:</b>	ASTM F 36 J	6-14 %
<b>rear suspension:</b>	ASTM F 36 J	>55 %
<b>Tensile strength:</b>	8 Mpa	
<b>oil resistance:</b>	very good	
<b>petrol resistance:</b>	good	
<b>acid resistance:</b>	not recommended	
<b>alkali resistance:</b>	conditional	
<b>permissions:</b>	DVGW, BAM	

Subject to alteration without prior notice.

All mentioned properties contained in this technical data sheet are guiding values representing longterm experience average.